

USES

- The mortar modified with this product have superior flexural compressive strength.
- Besides cement mortar and concrete it has very good adhesion to Wood and Metal.
- This product when mixed with cement mortar, works as curing compound does not need additional curing.
- This product can also be used on wet surfaces.

DESCRIPTION

This is an aqueous polymer emulsion and when mixed with cement mortars, it makes the modified mortar as hard, tough and durable. It is superior adhesive and gives impact strength. This is an excellent waterproofing compound. Capability and the mortar made with it are resistant to many industrial chemicals, UV light and heat.

APPLICATION

Silica Sand 200 kgs with Portland cement 100 kgs, total 300 kgs to be mixed with 120 kgs of Protekta-600

TECHINCAL DATA

Appearance : White, Milky liquid
pH : 9.5
Specific gravity : 1.058

IMPORTANT NOTE

Protekta products are non-hazardous when properly handled, stored and applied. When handling suitable protective clothing should be worn. The materials should not be ingested, inhaled or make skin contact. MSDS are available.

WARRANTY:

The information given in this data sheet is based on many years of experience and is correct to the best of our knowledge and should be used only as a guide. Tech Dry (India) Pvt Ltd reserves the right to alter certain product parameters within the spectrum of properties in order to keep abreast of technical advances. The information in this document is based on the present state of our knowledge and is applicable to the product. Tech Dry (India) Pvt Ltd is responsible for the quality of the product at the time of despatch but is not responsible for its quality after subsequent storage, handling and application. Neither Tech Dry (India) Pvt Ltd nor its associated companies shall be held liable for any damage resulting from the handling or from contact with the above product. See reverse side of invoice or packing slip for additional terms and conditions of sale.

Minimum film forming temperature: 10°C to 12°C

DOSAGE: 20-25 sq.ft per ltr

SHELF LIFE: 6 months in a closed uncontaminated container and should be used before the use-by-date printed on the container. However if the product is passed its used-by-date it is not necessarily unusable. A quality control should be performed on the properties relevant to the application or otherwise contact the manufacturer for further advice

STORAGE: To be stored in closed containers in a cool place and prevent from extremes of heat

HEALTH & SAFETY: Non-Hazardous, Non-toxic, Non-flammable

Tech-Dry (India) Pvt. Ltd.

769, Ground Floor, I Cross, I Stage, Indiranagar, Bangalore 560 0328, Ph: ++91-80-25255294 / 25255406,
Fax: ++91-80-25289159. E.mail: techdry@airtelbroadband.in, Website: www.techdryindia.com